CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: T- 4358

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2017-05-09-05** **Date: 11-05-17**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of Roads and Drains at JP Colony in ward no.02 of Yelahanka Sub Division.
Agency	:	Technical Manager (west), KRIDL, BBMP, Bangalore.
Customer's Reference	:	BBMP/EE(YNK.D)/W.O/114/2016-17
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	09-05-17
Sample ID No	:	2017-05-09-05-01
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	10-05-17

SLNo.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	2.45	–
2	Finess by Air permeablity method (m^2/kg, Min)	285.5	225m^2/kg, Min
3	Density (gm/cc)	3.24	–
4	Standard Consistency (%)	28.5%	Not specified
5	Initial Setting time	155 minutes	Not less than 30 minutes
6	Final Setting time	240 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1mm	Not more than 10 mm

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 30 days from the date of issue of test certificate

Prepared by
Harshitha

CIVIL Pro BANGALORE Sig..... Date.....

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: T- 4358

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	CP-2017-05-09-05 **Date: 07-06-17**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of Roads and Drains at JP Colony in ward no.02 of Yelahanka Sub Division.
Agency	:	Technical Manager (west), KRIDL, BBMP, Bangalore.
Customer's Reference	:	BBMP/EE(YNK.D)/W.O/114/2016-17
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	09-05-17
Sample ID No	:	2017-05-09-05-01
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 6, Determination of Compressive Strength, Clause 6
Date of test	:	10-05-17

Compressive Strength

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	3 Days	29.0N/mm^2	Not less than 27 N/mm^2
2	7 Days	38.0N/mm^2	Not less than 37 N/mm^2
3	28 Days	55.0N/mm^2	Not less than 53 N/mm^2

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

Prepared by
Harshitha

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL|
GEO TECHNICAL| PROJECT MANAGEMENT| SURVEYING SERVICES |

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2017-05-09-05** **Date: 12-05-17**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP,
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of Roads and Drains at JP Colony in ward no.02 of
Agency	:	Technical Manager (west), KRIDL, BBMP, Bangalore.
Customer Reference	:	BBMP/EE(YNK.D)/W.O/114/2016-17
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	09-05-17
Sample ID No	:	2017-05-09-05-02(a)
Sample Type/ Size	:	20mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	09-05-17

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:

Total weight taken : 5000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	40 mm	0	0	0	100	100
2	20 mm	214	214	4.3	95.7	90-100
3	10 mm	2435	2649	53.0	47.0	25-55
4	4.75 mm	2134	4783	95.7	4.3	0-10
5	Pan	217	5000	100	0	–

CIVIL Pro Sig..... Date..... BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2017-05-09-05** **Date: 12-05-17**

Sample ID No : 2017-05-09-05-02(a)

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	13.2	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	12.4	
3	Specific Gravity	2.69	–
4	Bulk Density(Loose) (Kg/l)	1.48	–
5	Bulk Density(Compacted) (Kg/l)	1.53	–
6	Water Absorption(%)	0.22	–
7	Aggregate crushing Value(%)	22.9	Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface.
8	Aggregate Impact Value(%)	22.1	30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Prepared by
Harshitha

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signature
Quality Manager

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2017-05-09-05** **Date: 12-05-17**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP,
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of Roads and Drains at JP Colony in ward no.02 of
Agency	:	Technical Manager (west), KRIDL, BBMP, Bangalore.
Customer's Reference	:	BBMP/EE(YNK.D)/W.O/114/2016-17
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	09-05-17
Sample ID No	:	2017-05-09-05-02(b)
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates)
		IS: 2386 :1963(Part - 1,3,4) RA2011
		IS 2386 Part 1: Particle Size and Shape
		IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption
		IS 2386 Part 4: Mechanical Properties
Date of test	:	09-05-17

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : **15000** **grams**

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	342	342	2.3	97.7	90-100
3	20 mm	5439	5781	38.5	61.5	30-70
4	10 mm	4579	10360	69.1	30.9	10-35
5	4.75 mm	4260	14620	97.5	2.5	0-5
6	Pan	380	15000	100.0	0	---

CIVIL Pro Sig Date BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2017-05-09-05** **Date: 12-05-17**

Sample ID No : 2017-05-09-05-02(b)

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	12.4	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	11.6	
3	Specific Gravity	2.67	–
4	Bulk Density(Loose) (Kg/l)	1.54	–
5	Bulk Density(Compacted) (Kg/l)	1.58	–
6	Water Absorption(%)	0.21	–

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

Prepared by
Harshitha

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

TEST REPORT OF FINE AGGREGATE

Lab ID	:	**CP-2017-05-09-05** **Date: 13-05-17**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of Roads and Drains at JP Colony in ward no.02 of Yelahanka Sub
Agency	:	Technical Manager (west), KRIDL, BBMP, Bangalore.
Customer's Reference	:	BBMP/EE(YNK.D)/W.O/114/2016-17
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	09-05-17
Sample ID No	:	2017-05-09-05-03
Sample Type	:	Fine Aggregate
Reference to BIS codes	:	IS 383 : 2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1, 3) RA2012 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption
Date of test	:	10-05-17
Total weight taken	:	1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	82	82	8.2	91.8	90-100	90-100	90-100	95-100
3	2.36 mm	133	215	21.5	78.5	60-95	75-100	85-100	95-100
4	1.18 mm	179	394	39.4	60.6	30-70	55-90	75-100	90-100
5	600 micron	186	580	58.0	42.0	15-34	35-59	60-79	80-100
6	300 micron	173	753	75.3	24.7	5-20	8-30	12-40	15-50
7	150 micron	156	909	90.9	9.1	0-10	0-10	0-10	0-15
8	Pan	91	1000	100.0	0.0	---	---	---	---
Result :The tested Sample Conforms to Grading Zone II									

CIVIL PRO Sig..... Date..... BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TEST REPORT OF FINE AGGREGATE

Lab ID : CP-2017-05-09-05

Date: 13-05-17

Sample ID No : 2017-05-09-05-03

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)		–
2	Specific Gravity		–
3	Material finer than 75 micron(%)		Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro BANGALORE Sig. Date

Prepared by
Harshitha

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TEST REPORT ON PHYSICAL REQUIREMENTS OF HALLOW CONCRETE BLOCKS

Date: 12-05-17

Lab ID	:	CP-2017-05-09-05
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of Roads and Drains at JP Colony in ward no.02 of Yelahanka Sub Division.
Agency	:	Technical Manager (west), KRIDL, BBMP, Bangalore.
Customer's Reference	:	BBMP/EE(YNK.D)/W.O/114/2016-17
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	09-05-17
Sample ID No	:	2017-05-09-05-04
Sample Type/Size	:	Hallow concrete blocks of size (400X200X200)mm
Reference to BIS codes	:	IS : 2185 (Part 1) : 2005(RA 2010) Concrete Masonry Specification Part 1:Hollow and Solid Concrete Blocks (Dimensions -Annex-B, Clause 9.2 and 10 , Block density Annex - C Clause 9.3 and10, Compressive strength Annex -D Clause 9.4 and 10, Water absorption Annex -E Clause 9.5 and 10)
Date of test	:	09-05-17

BLOCK DENSITY:

Sl. No.	Measurement of overall Dimensions of Individual Blocks			Overall Volume of the Block in Cubic Centimetres	Weight of Oven Dried Block in Kilograms to the nearest 10 Gram	Block Density in Kg/cum*10^6	Avg.Block Density in (Kg/cum)	As per IS 2185 (Part 1):2005 (RA 2010)
	Length	Breadth	Height					
	mm	mm	mm	(Cm^3)	Kg	Kg/m^3	Kg/m^3	
1	400	200	201	16080	22.560	1403.0	1423.8	Not less than 1500Kg/m^3
2	401	202	200	16200	23.100	1425.9		
3	402	202	203	16484	23.780	1442.6		

WATER ABSORPTION:

Sl. No.	Wet weight after water absorption	Dry weight (Oven dry)	Water Absorption	Avg.Water Absorption	As per IS 2185 (Part 1):2005 (RA 2010)
	kg	kg	%	%	
1	25.345	23.870	6.18	5.90	Shall not be more than 10% by mass
2	26.122	24.650	5.97		
3	25.322	23.990	5.55		

CIVIL Pro Sig..... Date..... BANGALORE

Lab ID : CP-2017-05-09-05

Date: 12-05-17

Sample ID No : 2017-05-09-05-04

DIMENSION ANALYSIS

Sl.no	Length mm	Breadth mm	Height mm	Requirement as per IS 2185(Part 1):2005
1	401	200	201	
2	400	202	202	
3	402	203	201	
4	400	201	202	
5	402	201	201	
6	402	203	200	
7	402	202	200	
8	401	203	200	
9	401	201	201	
10	401	201	202	
11	403	203	201	Length : ± 5mm Breadth : ± 3mm Height : ± 3mm
12	401	204	202	
13	403	202	201	
14	400	201	201	
15	400	200	200	
16	402	200	201	
17	400	202	201	
18	400	203	203	
19	401	201	201	
20	402	203	200	
Average of 20	401	202	201	

CIVIL Pro Sig..... Date..... BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Lab ID : CP-2017-05-09-05

Date: 12-05-17

Sample ID No : 2017-05-09-05-04

COMPRESSIVE STRENGTH:

Sl. No.	Size of Hallow block		Area	Failure Load	Compressive strength	Average Compressive strength
	Length	Breadth				
	mm	mm	(mm^2)	(KN)	N/mm^2	(N/mm^2)
1	401	200	80200	312.5	3.9	4.0
2	400	202	80800	332.3	4.1	
3	402	203	81606	312.2	3.8	
4	400	201	80400	319.4	4.0	
5	402	201	80802	330.4	4.1	
6	402	203	81606	325.3	4.0	
7	402	202	81204	310.4	3.8	
8	401	203	81403	339.3	4.2	

As per IS Requirements (Table 2, Clause 5.1, 5.2 and 9.4)

Compressive strength		
Grade	Minimum average	Minimum Individual units.
C (3.5)	3.5 N/mm^2	2.8 N/mm^2

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro BANGALORE Sig..... Date.....

FOR CIVIL Pro.

Prepared by
Harshitha

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2017-05-23-04**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of Roads and Drains at JP Colony in ward no.02 of Yelahanka Sub Division.
Agency	:	Technical Manager (west), KRIDL, BBMP, Bangalore.
Customer's Reference	:	BBMP/EE(YNK.D)/W.O/114/2016-17
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	23-05-17
Sample ID No	:	2017-05-23-04-01
Customer ID	:	Drain Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date: 25-05-17

Date of test : 25/05/2017

Sl. No.	Identification Mark	Grade of	Date of Casting	Date of Testing	Dimension (mm)	Cross (Sq.mm)	Weight (kg)	Failure (KN)	Compressive (N/mm^2)	Average (N/mm^2)
1	Drain Concrete	M20	18/05/2017	25/05/2017	150.11 X 150.14 X 150.19	22538	8.314	396.7	17.6	17.6
2	Drain Concrete	M20	18/05/2017	25/05/2017	150.22 X 150.25 X 150.29	22571	8.389	401.8	17.8	
3	Drain Concrete	M20	18/05/2017	25/05/2017	150.19 X 150.21 X 150.22	22560	8.352	390.3	17.3	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Prepared by
Harsitha

CIVIL Pro BANGALORE Sig. Date

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL|
GEO TECHNICAL| PROJECT MANAGEMENT| SURVEYING SERVICES|

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2017-05-23-04** **Date: 15-06-17**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of Roads and Drains at JP Colony in ward no.02 of Yelahanka Sub Division.
Agency	:	Technical Manager (west), KRIDL, BBMP, Bangalore.
Customer's Reference	:	BBMP/EE(YNK.D)/W.O/114/2016-17
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	23-05-17
Sample ID No	:	2017-05-23-04-02
Customer ID	:	Drain Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 15/06/2017

Sl. No.	Identification Mark	Grade of	Date of Casting	Date of Testing	Dimension (mm)	Cross (Sq.mm)	Weight (kg)	Failure (KN)	Compressive (N/mm^2)	Average (N/mm^2)
1	Drain Concrete	M20	18/05/2017	15/06/2017	150.17 X 150.21 X 150.23	22557	8.326	521.1	23.1	22.9
2	Drain Concrete	M20	18/05/2017	15/06/2017	150.22 X 150.18 X 150.20	22560	8.344	514.4	22.8	
3	Drain Concrete	M20	18/05/2017	15/06/2017	150.23 X 150.22 X 150.19	22568	8.312	512.3	22.7	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Prepared by
Harsitha

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2017-05-27-05** **Date: 29-05-17**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of Roads and Drains at JP Colony in ward no.02 of Yelahanka Sub Division.
Agency	:	Technical Manager (west), KRIDL, BBMP, Bangalore.
Customer's Reference	:	BBMP/EE(YNK.D)/W.O/114/2016-17
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	27-05-17
Sample ID No	:	2017-05-27-05-03
Customer ID	:	RCC
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	29/05/2017

Sl. No.	Identification Mark	Grade of	Date of Casting	Date of Testing	Dimension (mm)	Cross (Sq.mm)	Weight (kg)	Failure (KN)	Compressive (N/mm^2)	Average (N/mm^2)
1	RCC	M20	22/05/2017	29/05/2017	150.23 X 150.22 X 150.28	22568	8.421	413.0	18.3	18.4
2	RCC	M20	22/05/2017	29/05/2017	150.13 X 150.17 X 150.19	22545	8.322	421.6	18.7	
3	RCC	M20	22/05/2017	29/05/2017	150.22 X 150.29 X 150.22	22577	8.414	410.9	18.2	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Prepared by
Harsitha

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL|
GEO TECHNICAL| PROJECT MANAGEMENT| SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: T- 4358

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 19-06-17

Lab ID	:	CP-2017-05-27-05
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of Roads and Drains at JP Colony in ward no.02 of Yelahanka Sub Division.
Agency	:	Technical Manager (west), KRIDL, BBMP, Bangalore.
Customer's Reference	:	BBMP/EE(YNK.D)/W.O/114/2016-17
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	27-05-17
Sample ID No	:	2017-05-27-05-04
Customer ID	:	RCC
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 19/06/2017

Sl. No.	Identification Mark	Grade of	Date of Casting	Date of Testing	Dimension (mm)	Cross (Sq.mm)	Weight (kg)	Failure (KN)	Compressive (N/mm^2)	Average (N/mm^2)
1	RCC	M20	22/05/2017	19/06/2017	150.21 X 150.20 X 150.28	22562	8.378	505.4	22.4	22.9
2	RCC	M20	22/05/2017	19/06/2017	150.13 X 150.10 X 150.12	22535	8.243	516.0	22.9	
3	RCC	M20	22/05/2017	19/06/2017	150.21 X 150.25 X 150.22	22569	8.377	525.9	23.3	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Prepared by
Harsitha

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL|
GEO TECHNICAL| PROJECT MANAGEMENT| SURVEYING SERVICES|

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

TEST RESULTS OF STEEL

Lab ID	:	**CP-2017-05-12-01** **Date: 13-05-17**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of Roads and Drains at JP Colony in ward no.02 of Yelahanka
Agency	:	Technical Manager (west), KRIDL, BBMP, Bangalore.
Customer's Reference	:	BBMP/EE(YNK.D)/W.O/114/2016-17
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	12-05-17
Sample ID No	:	2017-05-12-01-01
Sample Type	:	JSW
Reference to BIS codes	:	IS 1786-2008, IS:1608-2005(RA 2011), IS 1599-2012.
Date of test:	:	12-05-17

Sl.No	Identification of sample	Grade of the sample	Diameter of the steel bar	Weight of the sample	Yield stress	Tensile strength	Elongation	Bend test	Rebend test
			(mm)	(kg/m)	(N/mm2)	(N/mm2)	(%)		
1	JSW	Fe500	8	0.392	549	686	20.0%	Satisfactory	Satisfactory
2	JSW	Fe500	10	0.612	576	692	19.5%	Satisfactory	Satisfactory

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or pa
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro BANGALORE Sig..... Date.....

FOR CIVIL Pro.

Prepared By:
Harshitha

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL|
GEO TECHNICAL| PROJECT MANAGEMENT| SURVEYING SERVICES|